# FIREFIGHTER PARTICULATE

# **IDEAL FOR**

- · Structural firefighters.
- · High-level protection from thermal risk such as flashover, contact and radiant heat.
- · It acts as a barrier for carcinogenic and harmful particles.
- Superior protection and comfort thanks to 2 layers of lightweight, breathable fabric blending DuPont<sup>™</sup> Aramid Fibres, Viscose FR<sup>®</sup>, Polyamide and Elastane plus an intermediate layer of DuPont<sup>™</sup> Nomex<sup>®</sup> Nano Flex \* non woven fabric.
- · With HeiQ Smart Temp cooling technology for a better comfort and reduction of heat exhaustion, fatigue and heat stroke risks.
- \* Located in those head areas with more exposure to contact with particles.

### **CERTIFICATIONS**



# EN 13911/17

|--|

PROTECTION AGAINST FIRE FOR FIREFIGHTERS					
EN ISO 13911:2017, Protective clothing for firefighters					
	Flame Spread	Heat transfer (Flame)	Heat Transfer (Radiation)	Heat Resistance	
Performance Levels	Pass	Pass	Pass	Pass	



PROTECTION AGAINST STATIC ELECTRICITY		EFFICIENCY OF BARRIER FLAT SHEET MEDIA - FLOWING			
EN 1149-5:2018, Protective clothing - Electrostatic properties			NFPA 1971.2	018	
Derformence Levele	Daga		0,10 Microns	0,50 Microns	1,00 Microns
Performance Levels	Pass	Performance Levels	>99%	>99%	>99%

This firehood is compatible with the following breathing masks and helmet:

- MASK with ref. FPS 7000, manufactured by Dräger Safety AG & Co.KGaA, Lübeck
- MASK with ref. MSA 3S, manufactured by MSA Europe GmbH, Switzerland.
  MASK with ref. SARI ref. 5511680, manufactured by Scott Health & Safety Ltd, United Kingdom.

#### **KEY FEATURES**



















FIRE RESISTANT

ANTISTATIC COMPATIBLE







COOLING EFFECT






DIMENSIONS 22 cm 14 cm

# **FABRICS COMPOSITION**

#### PACKAGING



WASHING MAINTENANCE SYMBOLS



52 cm





#### FIREFIGHTER PARTICULATE HOOD (LAMINATED FABRIC)

Mass per unit area:	469 g/m	$^{2}$ ± 5 %	
EN 12127:1997	409 g/m	± 5 %	
Air Permeability	72 mm/s	s ± 10 %	
EN ISO 9237:1995	72 111/3	, 10 %	
Thermal Resistance (RCT):	0,0683 m <sup>2</sup> K/V	V ± 10 %	
EN ISO 11092:2014	0,0683 m K/V	V ±10%	
Water Vapour Resistance (RET):		V ± 10 %	
EN ISO 11092:2014	8,75 m²Pa/V	V ±10%	
Bursting resistance (after 5 washes):	00415		
EN ISO 13938-1:1999	204 kPa	± 10 %	
Determination of dimensional change	n domestic washing and drying:		
EN ISO 5077:2008 LEI	GTHWISE ≤ ±3% CROSSWIS	E ≤ ±3%	
Wa	ing procedure 6N (Ta=60 ±3°C) according to IS	C 6330:2012	
Resistance to pilling:	3	2000 CYCLES	
ISO 12945-2:2020	-	2000 CTCLLS	
	is "Very severe pilling" and 5 is "No pilling".		
Determination of the abrasion resistant		>100000 CYCLES	
EN ISO 12947-2:2016 Testing pres	ire: 12 kPa Until the t	Until the first yarn broken	
Fastness rates:			
Colour fastness to domestic and com	ercial laundering:	4 - 5 *	
EN ISO 105-C06:2010			
Colour fastness to perspiration (Alkal	· · · · · · · · · · · · · · · · · · ·	4 - 5 *	
EN ISO 105-E04:2013	ACID	4 - 5 *	
Colour fastness to rubbing (Dry & We	: DRY	4 - 5 *	
EN ISO 105-X12:2016	WET	4 - 5*	
Colour fastness to sea water:		4 - 5 *	
EN ISO 105-E02:2013		+-5	
Colour fastness to artificial light:		5**	
EN ISO 105-B02:2014 Método 2		5	
* Fastness rates in a scale from 1 to 5 in	nich 1 is "Poor behaviour" and 5 is "Good be	haviour"	

\* Fastness rates in a scale from 1 to 5 in which 1 is "Poor behaviour" and 5 is "Good behaviour".

\*\* Fastness to artifical light rates in a scale from 1 to 8 in which 1 is "Very poor" and 8 is "Excellent"

#### FIREFIGHTER PARTICULATE HOOD (2 LAYER FABRIC)



Mass per unit area:	414 g/m	<sup>2</sup> ±5%	
EN 12127:1997	414 g/m	± 5 %	
Air Permeability	885 mm/s	± 10 %	
EN ISO 9237:1995	665 1111/5	± 10 %	
Thermal Resistance (RCT):	0,0734 m <sup>2</sup> K/W	/ ± 10 %	
EN ISO 11092:2014	0,0734 M K/W	£ 10 %	
Water Vapour Resistance (RET):	8,47 m <sup>2</sup> Pa/W	/ ± 10 %	
EN ISO 11092:2014	8,47 m Pa/W	/ ±10%	
Bursting resistance (after 5 washes):		. 10.0/	
EN ISO 13938-1:1999	105 kPa	± 10 %	
Determination of dimensional change in do	omestic washing and drying:		
EN ISO 5077:2008 LENGTH	WISE ≤ ±3% CROSSWISE	E ≤ ±3%	
Washing p	procedure 6N (Ta=60 ±3°C) according to ISC	0 6330:2012	
Resistance to pilling:	2	2000 CYCLES	
ISO 12945-2:2020	_	2000 CTOLL	
	ery severe pilling" and 5 is "No pilling".		
Determination of the abrasion resistance or		>100000 CYCLES	
EN ISO 12947-2:2016 Testing pressure: 1	2 kPa Until the f	Until the first yarn broken	
Fastness rates:			
Colour fastness to domestic and commerci	ial laundering:	4 - 5 *	
EN ISO 105-C06:2010		- 5	
Colour fastness to perspiration (Alkaline &	Acid): ALKALINE	4 - 5 *	
EN ISO 105-E04:2013	ACID	4 - 5 *	
Colour fastness to rubbing (Dry & Wet):	DRY	4 - 5 *	
EN ISO 105-X12:2016	WET	4 - 5*	
Colour fastness to sea water:		- 5 *	
EN ISO 105-E02:2013		F - 0	
Colour fastness to artificial light:		5**	
EN ISO 105-B02:2014 Método 2		5	
* Fastness rates in a scale from 1 to 5 in which	1 is "Poor behaviour" and 5 is "Good be	haviour"	

\* Fastness rates in a scale from 1 to 5 in which 1 is "Poor behaviour" and 5 is "Good behaviour".

\*\* Fastness to artifical light rates in a scale from 1 to 8 in which 1 is "Very poor" and 8 is "Excellent"